G. I. SINCE 1962 srl
Via G. Pascoli n. 2
27030 CASTELLO D'AGOGNA (PV) ITALY
Tel. +39 (0)384 565011 - Fax + 39 (0)384 565050
E-Mail: gestioni@gestioni-industriali.it

TECHNICAL CHARACTERISTIC

Test Method	Property	Requirements	Average values
UNI ISO 3376	Determination of tensile strength	≥ 10 N/mm^2	Long. 11.2 N/mm^2 Trasv. 10,8 N/mm^2
UNI ISO 3376	Determination of elongation	> 20 %	Long. 30 % Trasv. 38 %
EN 12771	Determination of tear strength	≥ 8 N / mm	Long. 8.6 N/mm Trasv. 8.8 N/mm
UNI EN 12772	Determination of dimension stability	≤ 2 %	< 2 %

Reconstituted Leather from vegetal tanned leather only.
Material for welt produced by automatic continuous system.

VAT IVT024490200604 – Iscr.Reg.Impr. di Alessandria – R.E.A. di Alessandra N. AL-256657 – Capitale Sociale €. 10.000 i.v.
M-SK-01 Rev. 1

G. I. SINCE 1962 srl
Via G. Pascoli n. 2
27030 CASTELLO D'AGOGNA (PV) ITALY
Tel. +39 (0)384 565011 - Fax + 39 (0)384 565050
E-Mail: gestioni@gestioni-industriali.it

Average Composition

Thickness	2.0 mm – 4.0 mm	4.5 mm – 6.0 mm
Vegetable tanned leather scraps	54%	50%
Natural latex	24%	28%
Fatting agent	8%	8%
Humidity	14%	14%
Density	0,98 – 1,20	0,96 – 1,0
Standard size rolls	Linear meter 50 – width cm 37	Linear meter 25 – width cm 35
Tolerance on thickness	± 0.1 mm	± 0.2 mm

The exclusive presence of leather scraps vegetable tanned only and the conformity of chemical substance as Chrome VI, Pentachorophenol, Azocolorants, Aromatic Ammins and Clorurate Substance, makes the material in accordance to Italian and Europeans rules for toxicity.
THE MATERIAL IS IN CONFORMITY WITH REACH LEGISLATION.

VAT IVT024490200604 – Iscr.Reg.Impr. di Alessandria – R.E.A. di Alessandra N. AL-256657 – Capitale Sociale €. 10.000 i.v.
M-SK-01 Rev. 1